

Work Order	3109.1
Setup-Code	180611-10290-2801-01



Test Report

JIS Z 2801:2012 (Mod)

Antimicrobial products – Test for antimicrobial activity and efficacy

Test Object:

Coated Leneta-Foil vs. E. coli DSM 1576



Work Order	3109.1
Setup-Code	180611-10290-2801-01

Report on Findings

Client: Address:	Nano-Care UK (Signo-Nanocare UK Ltd) PO Box 225, Oswestry, Shropshire, SY10 1DL, UK +44 1691 654 282				
Work order no.:	3109.1				
Test object:	Coated Leneta-Folie vs. E. coli DSM 1576				
Sample description:	lackierte Kunststofffolien				
Date of receipt of sample:	08.06.2018				
Type of test:	JIS Z 2801:2012 Antimicrobial products – Test for antimicrobial activity and efficacy				
Test Germ:	Escherichia coli DSM1576 ATCC8739 ISML CC 02/023				
Test laboratory:	QualityLabs BT GmbH				
Address:	Neumeyerstrasse 46a 90411 Nuremberg, Germany				
Setup-Code:	180611-10290-2801-01				
Sample material:	Leneta-Folie				
No. of pages in report:	7				
Report on findings Place a to the client: Recipi	· ·				
Laboratory Director:	Harald Gerauer, Laboratory Director QualityLabs BT GmbH				
Released:	Markus Zehe, Managing Director QualityLabs BT GmbH				

EN 24.09.2014 TN



Work Order	3109.1
Setup-Code	180611-10290-2801-01

Declaration on Quality Assurance

This investigation was performed and supervised according to the standard operating procedure "SOP zu JIS Z 2801:2012 (Mod)" by QualityLabs BT GmbH. The laboratory and process are continually monitored by independent, external authorities, as well as by internal audits.

Archiving

A copy of the test report, a protocol of the measurement as well as the accompanying correspondence and business records are archived by QualityLabs BT GmbH. The retention period is at least 10 years.

Test description

Anti-bacterial activity is determined in accordance with a modified version of JIS Z 2801:2012.

During the test, a thin liquid-film containing the bacteria $(1.25 \times 10^4 \, \text{CFU} \, / \, \text{cm}^2)$ is applied directly to the test sample (Standard: 5 cm x 5 cm). To avoid desiccation a foil (Standard: 4cm x 4cm, Stomacher Bags) is applied. Immediately after inoculation, the bacteria from the reference sample are separated from the sample and the enveloping foil surfaces using ultrasound and vortex devices and the number of viable germs (CFU – colony-forming units) is determined (t_0 value). A further set of reference samples and samples given anti-microbial treatment is incubated with bacteria in a liquid-film and the enveloping foil in a damp environment at 37°C. After 24 hours, the bacteria are separated from the sample surfaces using ultrasound and vortex devices and the number of viable germs is determined (t_{24} value).



Work Order	3109.1
Setup-Code	180611-10290-2801-01

Assessment of antimicrobial activity

A logarithmic germ reduction of ≥ 3 log scales of the antimicrobial sample in comparison to the respective reference is used as assessment criterion to pass the antimicrobial test.

Germ reduktion [log scales]	Antibacterial activity
< 3	Not sufficient antimicrobial activity
≥3	Sufficient antimicrobial activity



1
0-2801-01
(

References to Testconditions

Testconditions				
Sample size	25	cm ²		
Foil size	16	cm ²		
Volume Inoculum	400	μl		
Sample cleaning	Isopropanol	-		

References to deviations, preincubations, special test conditions

NONE



Work Order	3109.1
Setup-Code	180611-10290-2801-01

Test Results

	Sample Name	Sample Code		t ₀ (cells/cm²)		t	₂₄ (cells/cm²)	Reduction [%]	Log Reduction
1	Leneta-Folie P121-10 (Reference)	102900806180001	9.0 x 10 ⁴	1.1 x 10 ⁵	1.1 x 10 ⁵	5.1 x 10 ⁵	4.1 x 10 ⁵	5.3 x 10 ⁵	-	-
2	Liquid Guard clean + primer + wipe	102900806180002				< 1.0 x 10 ¹	< 1.0 x 10 ¹	< 1.0 x 10 ¹	> 99.99	> 4
3	Liquid Guard pro + wipe	102900806180003				< 1.0 x 10 ¹	< 1.0 x 10 ¹	< 1.0 x 10 ¹	> 99.99	> 4

^{*}see "Interpretation of Results", page 6

Test strain	Escherichia coli DSM1576 ATCC8739 ISML CC 02/023
Initial cell count inoculum / cm²	1.25 x 10⁴
Initials of the editor	MZ
Measurement ended on	Jun-15-2018



Work Order	3109.1
Setup-Code	180611-10290-2801-01

_				
Came	monte	On	toct	objects
1.011111	1161115		1651	ODIECIS

NONE

Interpretation of the results based on the measurements

NONE

Editor:	Mr. Zehe	Crosschecked:	Mr. Shendi	

References

JIS Z 2801:2012 Antimicrobial products - Test for antimicrobial activity and efficacy